



SCHULTE BUILDING SYSTEMS

PRODUCT TYPE	SUBSTRATE	PRODUCT COLOR	SHERWIN-WILLIAMS ITEM CODE	INITIAL SOLAR REFLECTANCE	AGED SOLAR REFLECTIVE EXPOSURE	INITIAL EMISSIVITY	SOLAR REFLECTIVE INDEX (SRI)	AGED SOLAR REFLECTIVE INDEX (SRI)
FLUROPON SR	GALVALUME	BONE WHITE		0.70	0.70	0.85	85	85
FLUROPON SR	GALVALUME	SNOW WHITE		0.65	0.62	0.86	78	74
FLUROPON SR	GALVALUME	SLATE GRAY		0.37	0.38	0.87	40	41
FLUROPON SR	GALVALUME	ALMOND		0.64	0.64	0.87	77	77
FLUROPON SR	GALVALUME	BROWNSTONE		0.48	0.48	0.88	55	55
FLUROPON SR	GALVALUME	CONLONIAL RED		0.31	0.30	0.86	31	30
FLUROPON SR	GALVALUME	REGAL RED		0.49	0.47	0.84	55	52
FLUROPON SR	GALVALUME	CLASSIC GREEN		0.32	0.31	0.86	33	31
FLUROPON SR	GALVALUME	GALLERY BLUE		0.28	0.28	0.86	27	27
FLUROPON SR	GALVALUME	MEDIUM BRONZE		0.34	0.33	0.87	36	35
FLUROPON SR	GALVALUME	MIDNIGHT BRONZE		0.29	0.28	0.87	29	28
POLYESTER SR	GALVALUME	POLAR WHITE		0.59	0.58	0.87	70	68
WEATHERXL SR	GALVALUME	CHARCOAL		0.37	0.36	0.86	39	38
WEATHERXL SR	GALVALUME	ASH GRAY		0.46	0.47	0.86	52	53
WEATHERXL SR	GALVALUME	BLACK		0.29	N/A	0.85	28	N/A

*Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Panels are unwashed. **These measurements are NOT intended to be used for ENERGY STAR certification.***

The SHERWIN-WILLIAMS COMPANY certifies these tests to be true and accurate and performed by our laboratory.



SCHULTE BUILDING SYSTEMS

PRODUCT TYPE	SUBSTRATE	PRODUCT COLOR	SHERWIN-WILLIAMS ITEM CODE	INITIAL SOLAR REFLECTANCE	AGED SOLAR REFLECTIVE EXPOSURE	INITIAL EMISSIVITY	SOLAR REFLECTIVE INDEX (SRI)	AGED SOLAR REFLECTIVE INDEX (SRI)
WEATHERXL SR	GALVALUME	BURNISHED SLATE		0.34	0.33	0.86	35	34
WEATHERX SR	GALVALUME	KOKO BROWN		0.35	0.35	0.86	37	37
WEATHERXL SR	GALVALUME	LIGHT STONE		0.56	0.56	0.86	65	65
WEATHERXL SR	GALVALUME	SADDLE TAN		0.47	0.47	0.86	53	53
WEATHERXL SR	GALVALUME	DESERT TAN		0.42	0.43	0.87	47	48
WEATHERXL SR	GALVALUME	EVERGREEN		0.35	0.34	0.86	37	35
WEATHERXL SR	GALVALUME	FERN GREEN		0.28	0.28	0.87	28	28
WEATHERXL SR	GALVALUME	COLONY GREEN		0.35	0.34	0.86	37	35
WEATHERXL SR	GALVALUME	HAWAIIAN BLUE		0.31	0.31	0.86	31	31
WEATHERXL SR	GALVALUME	RUSTIC RED		0.36	0.36	0.86	38	38
WEATHERXL SR	GALVALUME	BURGUNDY		0.28	0.27	0.86	27	26
WEATHERXL SR	GALVALUME	CRIMSON RED		0.39	0.38	0.85	42	40
WEATHERXL SR	GALVALUME	SOLAR WHITE		0.71	0.69	0.85	86	83
WEATHERXL SR	GALVALUME	AZTEC GOLD		0.53	0.51	0.86	61	58

*Solar reflectance values are determined by means of a solar spectrum reflectometer in accordance with ASTM C 1549. Thermal emittance values are determined in accordance with ASTM C 1371. SRI is calculated in accordance to ASTM E 1980 with medium wind speed. Panels are unwashed. **These measurements are NOT intended to be used for ENERGY STAR certification.***

The SHERWIN-WILLIAMS COMPANY certifies these tests to be true and accurate and performed by our laboratory.